## Amendments to the Claims:

The listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

1 - 39. (Cancelled)

40. (Currently Amended) A process for treating a fluorine compound-containing gas, comprising:

carbon and fluorine, (b) carbon, hydrogen and fluorine, (c) carbon, hydrogen, oxygen and fluorine, (d) SF<sub>6</sub>, and (e) NF<sub>3</sub>, wherein the concentration of the fluorine compound is 0.5 to 10% by volume, with a catalyst comprising alumina as an active compound and 7.2 to 49.4 wt.% of nickel oxide, said catalyst containing a composite oxide of aluminum and nickel;

adding steam or a reaction gas containing steam and oxygen to the gas stream; and

effecting a hydrolysis reaction between the at least one compound and the steam, thereby producing a treated gas containing hydrogen fluoride,

wherein the decomposition activity of the catalyst for fluorine compounds is maintained at a decomposition rate of about 80% or greater.

Serial No. 09/005,006

Amendment Dated: 04/23/2004

Reply to Office Action Mailed 12/23/2003

41. (Previously Presented) A process according to Claim 40, further

comprising washing the treated gas with water to remove the hydrogen fluoride.

42. (Previously Presented) A process according to Claim 40, further

comprising washing the treated gas with an alkaline solution or slurry to

neutralize the hydrogen fluoride and other acidic compounds.

43. (Previously Presented) A process according to Claim 40, further

comprising washing the treated gas with water and subsequently neutralizing

the water that has absorbed the hydrogen fluoride with an alkaline solution or

slurry.

44. (Previously Presented) A process according to Claim 40, wherein the

catalyst further comprises zinc oxide, and wherein a ratio of aluminum to a total

of nickel and zinc is 50 to 99: 50 to 1 by atom.

45. (Previously Presented) A process according to Claim 40, wherein the

catalyst consists essentially of alumina and nickel oxide and a composite oxide of

aluminum and nickel.

Page 3 of 16

Reply to Office Action Mailed 12/23/2003

46. (Previously Presented) A process according to Claim 40, wherein the

at least one compound is at least one compound selected from the group

consisting of CF<sub>4</sub>, C<sub>2</sub>F<sub>6</sub>, C<sub>3</sub>F<sub>8</sub>, C<sub>4</sub>F<sub>8</sub>, C<sub>5</sub>F<sub>8</sub>, CHF<sub>3</sub>, CH<sub>2</sub>F<sub>2</sub>, CH<sub>3</sub>F, C<sub>2</sub>HF<sub>5</sub>, C<sub>2</sub>H<sub>2</sub>F<sub>4</sub>,

 $C_2H_3F_3$ ,  $C_2H_4F_2$ ,  $C_2H_5F$ ,  $CH_2OCF_2$ ,  $SF_6$ , and  $NF_3$ .

47. (Previously Presented) A process according to Claim 40, wherein the

at least one compound is at least one compound selected from the group

consisting of CF<sub>4</sub>, C<sub>2</sub>F<sub>6</sub>, C<sub>3</sub>F<sub>8</sub>, C<sub>4</sub>F<sub>8</sub>, C<sub>5</sub>F<sub>8</sub>, CHF<sub>3</sub>, CH<sub>2</sub>F<sub>2</sub>, CH<sub>3</sub>F, C<sub>2</sub>HF<sub>5</sub>, C<sub>2</sub>H<sub>2</sub>F<sub>4</sub>,

 $C_2H_3F_3$ ,  $C_2H_4F_2$ ,  $C_2H_5F$ ,  $SF_6$ , and  $NF_3$ .

48. (Currently Amended) A method of treating a gas containing a

perfluoro-compound, comprising:

contacting the gas containing a fluorine compound in a concentration of

0.5 to 10% by volume at a temperature of 400 to  $800^{\circ}\mathrm{C}$  with a catalyst

comprising aluminum oxide as an active component and 7.2 to 49.4 wt.% of

nickel oxide, said catalyst containing a composite oxide of aluminum and nickel,

in the presence of steam, whereby the perfluoro-compound is decomposed by

hydrolysis to produce a treated gas containing hydrogen fluoride and acidic

compounds; and

contacting the treated gas with water to absorb the hydrogen fluoride and

the acidic compounds from the treated gas,

wherein the decomposition activity of the catalyst relative to fluorine compounds is maintained at a decomposition rate of about 80% or greater.

- 49. (Previously Presented) A process according to Claim 48, wherein the perfluoro compound is at least one compound selected from the group consisting of CF<sub>4</sub>, CHF<sub>3</sub>, C<sub>2</sub>F<sub>6</sub>, C<sub>3</sub>F<sub>8</sub>, C<sub>4</sub>F<sub>8</sub>, SF<sub>6</sub> and NF<sub>3</sub>.
- 50. (Previously Presented) A process according to Claim 48, wherein the catalyst further comprises zinc oxide, the balance being aluminum oxide.
- 51. (Previously Presented) A process according to Claim 48, wherein the catalyst consists essentially of alumina and nickel oxide and composite oxide of aluminum and nickel.

## 52 - 74. (Cancelled)

- 75. (Withdrawn) A process according to claim 40, wherein the compound in the gas stream is  $SF_6$ .
- 76. (Withdrawn) A process according to claim 40, wherein the compound in the gas stream is carbon, fluorine and hydrogen.

77. (Withdrawn) A process according to claim 40, wherein the compound in the gas stream is NF<sub>3</sub>.

78. (Withdrawn) A process according to claim 40, wherein the compound in the gas stream is at least one member selected from the group consisting of CHF<sub>3</sub>, CH<sub>2</sub>F<sub>2</sub>, CH<sub>3</sub>F, C<sub>2</sub>HF<sub>5</sub>, C<sub>2</sub>H<sub>2</sub>F<sub>4</sub>, C<sub>2</sub>H<sub>3</sub>F<sub>3</sub>, C<sub>2</sub>H<sub>4</sub>F<sub>2</sub>, C<sub>2</sub>H<sub>5</sub>F, CH<sub>2</sub>OCF<sub>2</sub>, SF<sub>6</sub> and NF<sub>3</sub>.

79. (Previously Presented) A process according to claim 40, wherein the fluorine compound-containing gas to be treated is used as etchants or cleaners for semiconductors.

80. (New) A process for treating a fluorine compound-containing gas, comprising:

contacting a gas stream containing at least one compound consisting of (a) carbon and fluorine, wherein the concentration of the fluorine compound is 2 to 10% by volume, with a catalyst comprising alumina as an active compound and 7.2 to 38.6 wt.% of nickel oxide, said catalyst containing a composite oxide of aluminum and nickel;

adding steam or a reaction gas containing steam and oxygen to the gas stream; and

effecting a hydrolysis reaction between the at least one compound and the

steam, thereby producing a treated gas containing hydrogen fluoride, wherein a

decomposition rate of the at least one compound is maintained at about 80% or

greater.

81. (New) A process for treating a fluorine compound-containing gas,

comprising:

contacting a gas stream containing at least one compound consisting of (a)

carbon and fluorine at a temperature from about 400 °C to about 800°C, wherein

the concentration of the fluorine compound is 0.5 to 10% by volume, with a

catalyst comprising alumina as an active compound and 7.2 to 38.6 wt.% of

nickel oxide, said catalyst containing a composite oxide of aluminum and nickel,

adding steam or a reaction gas containing steam and oxygen to the gas

stream; and

effecting a hydrolysis reaction between the at least one compound and the

steam, thereby producing a treated gas containing hydrogen fluoride, wherein a

decomposition rate of the at least one compound is maintained at about 80% or

greater.

82. (New) The process of claim 81, wherein said gas stream is contacted

with said catalyst at a temperature from about 400 °C to about 700°C.

Page 7 of 16

83. (New) A process for treating a fluorine compound-containing gas,

comprising:

contacting a gas stream containing at least one compound consisting of (a)

carbon and fluorine at a temperature from about 400 °C to about 700°C, wherein

the concentration of the fluorine compound is 0.5 to 10% by volume, with a

catalyst comprising alumina as an active compound and about 20 to about 30

wt.% of nickel oxide, said catalyst containing a composite oxide of aluminum and

nickel,

adding steam or a reaction gas containing steam and oxygen to the gas

stream; and

effecting a hydrolysis reaction between the at least one compound and the

steam, thereby producing a treated gas containing hydrogen fluoride, wherein a

decomposition rate of the at least one compound is maintained at about 95% or

greater.

84. (New) The process of claim 83, wherein said gas stream is contacted

with said catalyst at a temperature from about 400 °C to about 700°C.

Page 8 of 16